

Normal Bushing	Special Bushing
<ul style="list-style-type: none"> <li>• Hot work annealed steel (DIN 1.2343 / AISI H11)</li> <li>• Quenching in bath salt and tempering HRC 44-46</li> <li>• Superficial CLIN NIVE™ Super (Nitriding t= 300 µm)</li> <li>• Hardness HV 1050</li> </ul>	<p>As normal condition +</p> <ul style="list-style-type: none"> <li>• CLIN NIVE™ Super without oxidation</li> <li>• Special Vedani's Treatment</li> <li>• Hardness HV 2500</li> </ul>
<p><b>UP 30%</b></p>	

